

CERA VELAS PERFECTAS GV 20

FICHA TÉCNICA

Test Method	Units	Method	Specification
Congeaing Point	°C	ASTM D938	66 - 70
Needle Penetration 25°C	1/10 mm	ASTM D1321	14 - 16
Oil content		ASTM D721	Max 1
Viscosity 100°C	mm ² /s	ASTM D445	8 - 11
Color Saybolt		ASTM D156	25 - 30
Visual Color			white
RAL		GZ 041	conform
FDA		FDA 21 CFR 172.886	conform
REACH		EC 1907/2006	registered

Main Application: candles molded in silicon.

NOTICE: This product information is indicative and does not include any guarantee.