

GV-35

FICHA TECNICA

Special wax for container candles made of carefully selected raw materials;
One-pour blend;
Excellent wax adherence to the wall of the containers;
No shrinkage of the wax while cooling;
Smooth surface;
Evenly fragrance release while burning;
Optimal wax burning;

Technical parameters of the special wax E211 :	
Melting point	52 – 55°C
Penetration at 25 °C	50– 70 mm. 10^{-1}
Oil content %	0.5 – 1.0
Color Saybolt	+10 - +12

Short instructions for making container candles:

Pouring temperature of the candles should be at temperature of **65 °C**;
Heating of the containers before pouring at **40 °C** ;
The containers should be clean for optimal wax adherence to the walls;
The cooling of the candles should not be fast, but smooth;